## SPECIFICATION CONTROL DRAWING

44A0212

TITLE

WIRE, RADIATION-CROSSLINKED, POLYALKENE-INSULATED, LIGHT WEIGHT, GENERAL PURPOSE, 1000 VOLT

Date 12-7-05

evision

94.5


150.

.254 ± .007

 $.308 \pm .008$ 

D

This specification sheet forms a part of the latest issue of Raychem Specification 44 and MIL-W-81044 as applicable.



WIRE

SIZE (AWG)

26

24

20

18

16

14

10

8

6

4

133 x 27

133 x 25

PART NUMBER

<u>1</u>/

44A0212-26-\*

44A0212-24-\*

44A0212-22-\* 44A0212-20-\*

44A0212-18-\*

44A0212-16-\*

44A0212-14-\*

44A0212-12-\* 44A0212-10-\*

44A0212- 8-\*

44A0212- 6-\*

44A0212- 4-\*

JACKET-RADIATION-CROSSLINKED, MODIFIED PVF<sub>2</sub> Thickness: .004 ± .001 in.

TABLE I. CONSTRUCTION DETAILS								
	MAXIMUM	FINISHED WIRE						
CONDUCTOR STRANDING (number x AWG)	DIAMETER STRANDED CONDUCTOR (in.)	MAXIMUM RESISTANCE AT 20°C (ohms/1000ft.)	DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft.)				
19 x 38	.021	38.4	.040 ± .002	1.6				
19 x 36	.026	24.3	$.046 \pm .002$	2.4				
19 x 34	.033	15.1	.054 ± .002	3.5				
19 x 32	.041	9.19	.062 ± .002	5.1				
19 x 30	.052	5.79	.073 ± .003	7.7				
19 x 29	.058	4.52	.081 ± .003	9.8				
19 x 27	.072	2.88	.098 ± .004	14.7				
37 x 28	.090	1.90	.117 ± .004	22.1				
37 x 26	.118	1.19	.146 ± .004	35.6				
133 x 29	.176	.658	.206 ± .006	61.8				
19 x 36 19 x 34 19 x 32 19 x 30 19 x 29 19 x 27 37 x 28 37 x 26	.026 .033 .041 .052 .058 .072 .090	24.3 15.1 9.19 5.79 4.52 2.88 1.90 1.19	.046 ± .002 .054 ± .002 .062 ± .002 .073 ± .003 .081 ± .003 .098 ± .004 .117 ± .004 .146 ± .004	2.4 3.5 5.1 7.7 9.8 14.7 22.1 35.6				

418

264

TABLE II. PERFORMANCE DETAILS							
	BENDTESTING						
PART NUMBER 1/	MANDREL DIAMETER (inch) (± 3%)			WEIGHT (lb) (± 3%)			
	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND		
44A0212-26-*	.500	.750	.250	.375	1.00		
44A0212-24-*	.500	1.00	.250	.375	2.00		
44A0212-22-*	.750	1.00	.250	.375	2.00		
44A0212-20-*	.750	1.00	.250	.500	3.00		
44A0212-18-*	1.00	1.50	.375	.500	3.00		
44A0212-16-*	1.00	1.50	.375	1.00	4.00		
44A0212-14-*	1.50	2.00	.500	1.00	4.00		
44A0212-12-*	2.00	2.00	.500	1.50	4.00		
44A0212-10-*	3.00	3.00	.750	2.00	4.00		
44A0212- 8-*	3.00	4.00	.750	3.00	5.00		
44A0212- 6-*	4.00	5.00	1.00	3.00	8.00		
44A0212- 4-*	5.00	6.00	1.25	3.00	8.00		

218

272

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

 $\underline{1}/\text{COLORS}$  AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL

Page 1 of 2

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297

D

## WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature VOLTAGE RATING: 1000 volts (rms) at sea level ACCELERATED AGING: 300 ± 2°C for 6 hours Identification legibility, 225 ± 2°C for 6 hours

BLOCKING:  $150 \pm 2$ °C for 24 hours

COLOR: White preferred

FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum); no flaming of facial tissue HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IDENTIFICATION AND STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Elongation, 150% (minimum)

Tensile Strength, 2500 lbf/in<sup>2</sup> (minimum)

**INSULATION FLAWS:** 

Primary Insulation,

SparkTest, 2.0 kV (rms)

Impulse DielectricTest, 6.0 kV (peak)

Finished Wire;

SparkTest, 4.0 kV (rms) at 3 kHz Impulse DielectricTest, 8.0 kV (peak)

INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

LIFE CYCLE: 200 ± 2°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours

SHRINKAGE: 300 ± 2°C, 0.125 in. (maximum) in 12 in., AWG 26-12

300 ± 2°C, 0.250 in. (maximum) in 12 in., AWG 10-4

SMOKE: 200 ± 2°C, No visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings THERMAL SHOCK RESISTANCE: 150 ± 2°C, 0.060 in. (maximum)

VOLTAGE WITHSTAND TEST (Post Environmental): 3000 volts (rms), 60 Hz, 5 minutes

WICKING: 2.25 in. (maximum)

PART NUMBER: The "\*" in the part numbers on page 1 shall be replaced by color code designators.

1/ Example: AWG 20, white: 44A0212-20-9

 $\underline{1}$ / See footer section on page 1